



**MARICOPA COUNTY**  
*Department of Transportation*

MEMORANDUM

**Date:** June 4, 2014 Revised 2014-09-10  
**To:** MAG Specifications and Details Committee  
**From:** Robert Herz, MCDOT Representative  
**Subject:** Revisions to Section 321 from MCDOT Supplement **Case 14-13**

**PURPOSE:** Incorporate MCDOT enhancements to Section 321 PLACEMENT AND CONSTRUCTION OF ASPHALT CONCRETE PAVEMENT into the MAG Specifications.

**REVISIONS:**

- 321.8 – Added requirement for adjacent facilities to be in acceptable condition prior to commencing with asphalt paving operations.
- 321.8.2 – Added tack coat requirement for traverse joints with existing pavement.  
– Adjusted requirements for longitudinal construction joints to not deviate more than ¼ inch from a 12-foot straightedge positioned in any direction.
- 321.8.4 – Added disclaimer: The minimum temperatures in Table 321-2 do not guarantee that the asphalt mix will be compacted to the required density. The contractor is responsible to achieve the required compaction.
- 321.8.10 – Added new section for the protection of asphalt base courses on arterial roadways.
- 321.9 – Referee Testing requests are required to be based on valid Quality Control Test results.
- 321.10.1 – Revised the definition for subplot and  
– Clarified that the Acceptance Laboratory is to be provided by the contracting agency.  
– **Added the following technician requirement for acceptance laboratories: *The laboratory shall use properly certified technicians in accordance with ASTM D3666, Section 7 (Personnel Qualifications).***
- ~~321.10.3 – Added pavement removal criteria that prevents full depth pavement cuts to be located within a lane wheel path and prevents creation of narrow pavement edge strips. PROPOSED CHANGE DELETED~~
- 321.10.4 – Added corrective measures to be taken when total pavement thickness deficiency is 0.50 inches or greater for agency contracted work.  
– The existing specification is unclear as to if the thickness penalty is to be applied to each individual layer of a multi-layer pavement or if the acceptance and penalty provisions are to be applied to the total composite asphalt section. The text and Table 321-6 have been adjusted such that the penalty is only applied to the total final asphalt pavement thickness not to individual layers.
- 321.10.6 – Adjusted Table 321-9 to correspond with the 2014 revisions made to Tables 321-5 and 321-8.
- 321.11 – Revised requirements for referee testing.
- 321.14.3 & 321.14.4 – Revised ASTM D5361-05 to ASTM D5361. The 2005 version had been superseded in 2006 and then again updated in 2014.**

Changes in section 321 made after the September 3, 2014 committee meeting are shown above as bolded.



**PLACEMENT AND CONSTRUCTION OF ASPHALT CONCRETE PAVEMENT****321.1 DESCRIPTION:**

This section is to provide specifications for furnishing all materials, mixing at a plant, hauling and placing a mixture of aggregate materials, mineral admixture and asphalt binder to form a pavement course for placement upon a previously prepared base or sub base.

**321.2 MATERIALS AND MANUFACTURE:**

The materials shall conform to Section [710](#) for the type specified. The specific required mix type shall be called out in the contract documents or as directed by the Engineer.

**321.3 WEATHER AND MOISTURE CONDITIONS:**

Asphalt concrete shall be placed only when the surface is dry, and when the atmospheric temperature in the shade is 40 degrees F. (50 degrees F for Asphalt Concrete lift less than 2 inch thick) or above. No asphalt concrete shall be placed when the weather is foggy or rainy, or when the base or sub base on which the material is to be placed is unstable. Asphalt concrete shall be placed only when the Engineer determines that weather conditions are suitable.

**321.4 APPLICATION OF TACK COAT:**

A tack coat shall be applied to all existing and to each new course of asphalt concrete prior to the placing of a succeeding lift of asphalt concrete. The tack coat may be deleted when a succeeding layer of asphalt concrete is being applied over a freshly laid course that has been subjected to very little traffic when approved by the Engineer.

The application of the tack coat shall comply with Section [329](#). The grade of emulsified asphalt shall be SS-1-h or CSS-1-h as specified in Section [713](#).

The same material that is specified above for the tack coat shall be applied to the vertical surfaces of existing pavements, curbs, and gutters, against which asphalt concrete is to be placed.

The surface to be covered may require repair or patching as directed by the Engineer. This shall be addressed in the project specifications prior to the bidding of the project.

**321.5 MIX DESIGN**

The mix design shall be submitted to the Engineer at least five working days prior to the start of asphalt concrete production. Mix designs provided by the agency may be utilized on projects at the Engineer's discretion. The Engineer will review and approve the mix design to assure it contains all of the required information as outlined in Section [710.3.1](#). The target values for gradations, binder contents, and air voids will be established as the accepted Job Mix Formula (JMF) based upon the mix design. Mix designs not containing all of the information will be returned within five working days of receipt of all mix design information, for action and resubmission by the contractor.

Once the mix design has been approved by the agency and the mixing plant selected, the Contractor and/or his supplier shall not change plants nor utilize additional mixing plants without prior approval of the Engineer.

If the contractor elects to change its source of material, the contractor shall furnish the Engineer with a new mix design, which meets the requirements of Section [710](#), as amended by the Project Specifications.

The contractor may make self-directed target changes to the approved mix design within the limits shown below. Requests for self-directed target changes shall be made in writing and acknowledged by the Engineer prior to the start of production of a lot and will remain in effect until such time as any additional changes are implemented. The self-directed target changes must meet the contract requirements for mix design criteria and gradation limits.

| <b>TABLE 321-1<br/>ALLOWABLE SELF-DIRECTED TARGET CHANGES</b> |   |
|---|---|
| MEASURED<br>CHARACTERISTICS                                   | ALLOWABLE SELF-DIRECTED<br>TARGET CHANGES |
| Gradation (Sieve Size)  |   |
| 3/8 inch  | ± 4% from mix design target value         |
| No 8  | ± 4% from mix design target value         |
| No 40   | ± 2% from mix design target value         |
| No 200  | +0.5% from mix design target value        |
| Binder Content  | ± 0.2% from mix design target value       |
| Effective Air Voids   | None                                      |

The contractor may propose target changes, other than self-directed changes, to the approved mix design for the approval of the Engineer. The Engineer will determine if the proposed target change will result in mix production that meets the contract requirements for mix design criteria and gradation limits. The target changes will not be retroactive for the purpose of acceptance.

### **321.6 MIX PRODUCTION:**

All materials shall be proportioned by weight in a hot mix asphalt plant in the proportions required by the mix design to provide a homogeneous and workable mass. Each hot mix asphalt plant shall be inspected in accordance with the provisions contained in the 'Hot Mix Asphalt Production Facilities' by the Arizona Rock Products Association and shall have a current inspection certificate. All measuring devices shall be calibrated at least annually by a technician licensed by the Arizona Bureau of Weights & Measures. Mixing plants shall conform to the requirements of AASHTO M-156, except as modified herein.

In drum mix plants the mineral admixture shall be added and thoroughly mixed with the mineral aggregate by means of a mechanical mixing device prior to the mineral aggregate and mineral admixture entering the dryer. The moisture content of the combined mineral aggregate shall be a minimum of three percent by weight of the aggregate during the mixing process.

For drum-mix plants, the mineral admixture shall be weighed across a weight belt, or other approved alternative weighing system, with a weight totalizer prior to entry into the mechanical mixing device. The mechanical mixing device shall be a pugmill type mixer that is in good working condition. The rate of the aggregate feed shall not exceed the mixing device's capacity in ton per hour. The mixer shall be constructed to minimize the loss of mineral admixture and shall be located in the aggregate delivery system at a location where the mixed material can be readily inspected. The mixing device shall be capable of effective mixing in the full range of the asphalt concrete production rates.

The hot plant and equipment shall be constructed and operated to prevent loss of mineral admixture through the dust collection system of the plant.

A positive signal system shall be provided and utilized during production whereby the mixing shall automatically be stopped if the mineral admixture is not introduced into the mineral aggregate. The plant will not be permitted to operate unless the signal system is in good working condition.

The introduction of bituminous material shall be controlled by an automated system fully integrated with the controls or the mineral aggregate and mineral admixture. The production of the plant shall be controlled by the rate required to obtain a uniform mixture of all components. Drying and heating shall be accomplished in such a manner as to preclude the mineral admixture from becoming coated with un-spent fuel. The completed asphalt concrete may be held in storage for up to 12 hours in insulated or heated silos, providing the minimum temperature noted herein for placement and compaction is met behind the placement device. If the Engineer determines that there is an

excessive amount of heat, heat loss, drain down, segregation and/or oxidation of the mixture due to temporary storage, use of surge bins or storage bins will be discontinued.

The temperature of the asphalt concrete, with unmodified binders, upon discharge from the mixer shall not exceed 335 degrees F. The discharge temperature may be increased on the recommendation of the binder supplier, when approved by the Engineer. If the asphalt concrete is discharged from the mixer into a hopper, the hopper shall be constructed so that segregation of the asphalt concrete will be minimized.

### **321.7 TRANSPORTATION:**

Petroleum distillates or other substances that will have a detrimental effect on the asphalt concrete shall not be used as a release agent.

The beds of all transportation units shall be clean and smooth to allow the free flow of material into the paving machine's hopper.

Tarpaulins shall be furnished on all trucks and used when weather condition warrant, or if directed by the Engineer.

### **321.8 PLACEMENT:**

Placement of asphalt concrete pavement shall not commence until authorized by the Engineer. The Engineer's authorization to allow commencement of asphalt concrete paving will generally require all newly constructed valley gutters, curbing, and curb and gutters which new pavement is to be placed against to be in-place and in an acceptable condition. While it is preferred to have all newly constructed concrete items against which new pavement is to be placed be in an acceptable condition, the Engineer may allow paving to commence based on weather, the amount of defective concrete, or other considerations.

**321.8.1 Placing:** All courses of asphalt concrete shall be placed and finished by means of a self-propelled paving machine equipped with an automatically actuated control system, except under certain conditions or at locations where the Engineer deems the use of a self-propelled paving machine impracticable.

The control system shall control the elevation of the screed at each end by controlling the elevation of one end directly and the other end indirectly either through controlling the transverse slope or alternatively when directed, by controlling the elevation of each end independently.

The control system shall be capable of working with one of the following devices:

- (a) Ski or non-contact device of not less than 30 feet in length, supported throughout its entire length
- (b) Taut stringline or wire set to grade
- (c) Short ski or sonar sensing units from curb control
- (d) Joint matching shoe

Failure of the control system to function properly shall be cause for the suspension of asphalt concrete production. In order to achieve a continuous operation, the speed of the paving machine shall be coordinated with the hot mix plant and transport units.

If the asphalt concrete is dumped from the hauling vehicles directly into the paving machine, care shall be taken to avoid jarring the machine or moving it out of alignment. No vertical load shall be exerted on the paving machine by the truck.

If asphalt concrete is dumped upon the surface being paved and subsequently loaded in the paving machine, the loading equipment shall be self-supporting and shall not exert any vertical load on the paving machine. Substantially all of the asphalt concrete shall be picked up and loaded into the paving machine.

Self-propelled paving machines shall spread the mixture without segregation or tearing, true to line, grade and crown indicated on the Project plans. Pavers shall be equipped with hoppers and augers that will distribute the mixture uniformly in front of an adjustable floating screed. The raising of the hopper wings must be minimized and

the paving machine will not be operated when in an empty condition.

Screeds shall include any strike-off device operated by tamping or vibrating action which is effective, without tearing, shoving or gouging the mixture and which produces a course with a uniform texture and density for the full width being paved. Screeds shall be adjustable as to height and crown and shall be equipped with a controlled heating device for use when required. In the case of the screed, auger extensions and vibrators shall be installed wherever the screed is extended more than one (1) foot beyond the end of the base auger or auger extension. However, when placing material against an extremely uneven curb or edge over a short distance, the Engineer may waive the auger extensions and vibrators.

At any place not accessible to the roller, the mixture shall be thoroughly compacted with tampers to provide a uniform and smooth layer over the entire area compacted in this manner.

**321.8.2 Joints:** Transverse joints, before a surface course is placed in contact with a cold transverse construction joint, the cold existing asphalt concrete shall be trimmed to a vertical face for its full depth ~~and~~ exposing a fresh face. The fresh face shall be tack coated prior to placement of the new asphalt concrete. After placement and finishing the new asphalt concrete, both sides of the joint shall be dense and the joint shall be smooth and tight. The surface in the area of the joint shall not deviate more than 1/4 inch from a 12-foot straightedge, when tested with the straightedge placed across the joint, parallel to the centerline.

Longitudinal joints of each asphalt course shall be staggered a minimum of 6 inches with relation to the longitudinal joint of the immediate underlying course's cold ~~transverse-longitudinal~~ construction joint.

Longitudinal joints with the cold existing or cold (more than 32 hours old) asphalt concrete shall require the existing pavement to be trimmed to a vertical face for its full depth ~~and~~ exposing a fresh face. The fresh face shall be tacked prior to placement of the adjacent course. Longitudinal joints with an existing asphalt pavement that is less than 32 hours old that has had its edge protected from damage may have adjacent new asphalt concrete placed after applying the required tack coat. After placement and finishing ~~the new asphalt concrete of longitudinal joints~~, both sides of the joint shall be dense and the joint shall be smooth and tight. The surface in the area of the joint shall not deviate more than 1/4 inch from a 12-foot straightedge, when tested with the straightedge placed across the joint, ~~parallel to the centerline in any direction.~~ The joint will be tack coated if required by the Engineer.

**321.8.3 Asphalt Leveling Course:** A leveling course shall be used when specified, or as directed in writing by the Engineer, to bring existing pavement to a uniform grade prior to placing an overlay or other course. If a leveling course is being applied on an Asphalt surface, a tack coat shall be applied. The compaction requirements contained in Section [321.10](#) do not apply to leveling courses.

**321.8.4 Compaction; Asphalt Base Course and Surface Course:** It is the contractor's responsibility to perform ~~any desired~~ Quality Control monitoring and/or testing during compaction operations to achieve the required compaction. The temperature of the asphalt concrete immediately behind the laydown machine shall meet the minimum requirements of Table [321-2](#). A probe type electronic thermometer with a current calibration sticker attached will be used to measure the temperature of the asphalt concrete mixture. When measuring the temperature of the mat, the probe shall be inserted at mid-depth and as horizontal as possible to the mat. The minimum temperatures in Table 321-2 do not guarantee that the asphalt mix will be compacted to the required density. The contractor is responsible to achieve the required compaction.

| <b>MINIMUM ASPHALT CONCRETE PLACEMENT TEMPERATURE</b> |                        |     |     |       |     |               |
|---|------------------------|-----|-----|-------|-----|---------------|
| Base <sup>(1)</sup> Temp (°F)                         | Mat Thickness (inches) |     |     |       |     |               |
|   | 1/2                    | 3/4 | 1   | 1 1/2 | 2   | 3 and greater |
| 40 – 50   | ---                    | --- | 310 | 300   | 285 | 275           |
| 50 – 60   | ---                    | 310 | 300 | 295   | 280 | 270           |
| 60 – 70   | 310                    | 300 | 290 | 285   | 275 | 265           |
| 70 – 80   | 300                    | 290 | 285 | 280   | 270 | 265           |
| 80 – 90   | 290                    | 280 | 270 | 270   | 265 | 260           |

|     |     |     |     |     |     |     |
|-----|-----|-----|-----|-----|-----|-----|
| +90 | 280 | 275 | 265 | 265 | 260 | 255 |
|-----|-----|-----|-----|-----|-----|-----|

- (1) Base on which mix is to be placed

Asphalt compaction equipment shall be of sufficient size and weight to accomplish the required compaction. All compaction equipment shall be operated and maintained in accordance with the manufacturer's recommendations and the project requirements. During the rolling operation, the speed of the roller shall not exceed 3 miles per hour, unless otherwise approved by the Engineer.

Pneumatic tired compactors shall be equipped with skirt-type devices mounted around the tires so that the temperature of the tires will be maintained during the compaction process.

The Engineer will determine the acceptability of the pavement compaction in accordance with Section [321.10](#).

**321.8.5 Smoothness:** The completed surfacing shall be thoroughly compacted, smooth and true to grade and cross-section and free from ruts, humps, depressions or irregularities. An acceptable surface shall not vary more than one-fourth (1/4) inch from the lower edge of a 12-foot straightedge when the straightedge is placed parallel to the centerline of the roadway.

**321.8.6 Asphalt Concrete Overlay:** Asphalt concrete overlay consists of the placing and compacting plant mix asphalt concrete over existing pavement. The mix design and thickness of the overlay shall be as shown on the plans or as specified in the special provisions.

Except when the existing asphalt surface is to be preheated and remixed, pavement surfaces shall be prepared as follows:

- (a) Areas designated for pavement repair by the contract documents (which may include severely raveled areas, severely cracked areas, over-asphalted areas, and other defects) shall be cut out and replaced. Pavement repairs shall be completed and approved before placing asphalt concrete overlay.
- (b) Before placing asphalt concrete overlay, milling shall be done as shown on the plans or specified in the special provisions and shall be in accordance with Section [317](#).
- (c) After pavement repairs and milling have been completed the entire surface shall be cleaned with a power broom.
- (d) After surfaces have been prepared to the satisfaction of the Engineer, they shall receive a tack coat per Section [321.4](#). Traffic will not be permitted to travel over surfaces which have received a tack coat, except when tack coat is applied to milled surfaces in compliance with Section [317.2](#) for dust control purposes. When the overlay is to extend onto a concrete gutter, the gutter shall be thoroughly cleaned of loose dust and cement particles and shall be tack coated.

Asphalt concrete overlay shall be placed as specified in Section [321.8.1](#) and compacted as specified in Section [321.8.4](#). The surface smoothness shall meet the tolerances specified in Section [321.8.5](#).

Frames and covers of manholes, survey monuments, valve boxes, clean-outs and other existing structures shall be adjusted in accordance with Section [345](#) to set flush with the finished surface of the new pavement. During adjustment if pavement or base materials are removed or disturbed, they shall be replaced with approved materials installed in a manner acceptable to the Engineer.

On roads without curb and gutter, the existing unpaved shoulder elevation shall be adjusted by the Contractor to match the elevation at the edge of the new overlay and slope away from the new pavement surface at a rate that the existing quantity of shoulder material will allow. Shoulder material shall be compacted to a minimum of 95% of maximum density, determined in accordance with Section [301.3](#). Shoulder adjustment to match the new pavement surface elevation shall not be measured. The cost of shoulder adjustment shall be included in the price paid for the asphalt concrete overlay or other related pay items. When the Engineer determines an insufficient amount of

material is available for shoulder adjustment, the Engineer may require the Contractor to provide additional material. Acceptable material for shoulders includes the existing shoulder material, millings, untreated base materials, or a granular material approved by the Engineer. Engineer requested imported material for shoulder adjustment is not included in the price paid for the asphalt concrete overlay.

**321.8.7 Pavement Fabric Interlayer:** Pavement fabric interlayer shall be used only when specified on the plans or in the specifications.

Pavement fabric interlayer shall be in accordance with Table [796-1](#) and be the class designated on the plans or in the specifications.

Asphalt binder coat used to bond the fabric to the pavement shall be paving asphalt PG 70-10 asphalt cement conforming to the requirements of Section [711](#). The application and distributing equipment for the asphalt binder shall conform to the requirements of Section [330](#). The asphalt binder coat shall be uniformly spray applied to the prepared pavement surface at the rate of 0.20 gallons per square yard for Class B fabric or at the rate of 0.25 gallons per square yard for Class A fabric. Some underlying surfaces may require a higher or lower application rate. A test strip may be necessary to determine the proper application rate. The width of liquid asphalt cement application shall be the fabric width, plus six inches.

Neither the asphalt binder coat or fabric interlayer shall be placed when weather conditions, in the opinion of the Engineer, are not suitable. The asphalt binder and fabric interlayer shall only be placed when the pavement is dry, the ambient air temperature is 50 degrees F and rising, and pavement temperature is 40 degrees F and rising.

Equipment for placing the fabric shall be mechanized and capable of handling full rolls of fabric. The equipment shall be able to lay the fabric smoothly to maximize pavement contact and remove air bubbles. Stiff bristle brooms shall be used to smooth the fabric. The equipment used to place the fabric shall be in good working order and is subject to approval by the Engineer.

Pavement fabric interlayer shall not be placed if the in-place binder is hotter than 325 degrees F or has cooled to 180 degrees F or below (as determined by non-contact thermometer).

Pavement fabric interlayer shall be placed onto the asphaltic binder with the heat bonded side up with a minimum amount of wrinkling or folding. Remaining wrinkles or folds 1-inch and larger shall be removed or slit and shingle-lapped in the direction of paving. Burning or torching of wrinkles is not allowed. Fabric shall overlap three to six inches to insure full closure of the joint. Transverse joints shall be shingle-lapped in the direction of paving to prevent edge pickup by the paver. A second application of hand-placed asphalt binder may be required at laps and repairs as determined by the Engineer to ensure proper binding of the narrow double fabric layer.

All areas where fabric has been placed shall be paved with asphaltic concrete during the same workshift. Placement of the asphaltic concrete shall closely follow fabric lay down. The temperature of the asphaltic concrete immediately behind the laydown machine shall not exceed 325 degrees F. In the event that the asphalt binder coat bleeds through the fabric causing construction problems before the overlay is placed, the affected areas shall be sanded with a sand blotter in compliance with Section [333](#). Excess sand shall be removed before beginning the paving operation. In the event of rainfall prior to the placement of the asphaltic concrete, the fabric shall be allowed to dry before the asphalt concrete is placed.

Turning of the paving machine or of other vehicles on the fabric shall be gradual and kept to a minimum to avoid damage to the fabric. Should equipment tires stick to the fabric during pavement operations, small quantities of paving asphalt concrete shall be broadcast on the fabric to prevent pick-up. Decrease of binder rate in order to minimize pick-up on tires is not allowed.

**321.8.8 Thickened Edge:** When the depth of the thickened edge extends four inches or more below the bottom of the asphalt pavement, the portion of the thickened edge extending below the asphalt pavement shall be placed and compacted prior to placement of the asphalt pavement. Placement of tack coat on the surface of the compacted thickened edge asphalt may be omitted when additional asphalt pavement is placed on the same day and the Engineer agrees that the surface of the thickened edge asphalt has remained clean.



When the depth of the thickened edge extends less than four inches below the bottom of the asphalt pavement, the portion below the asphalt pavement may be placed and compacted with the asphalt pavement in a single operation.

**321.8.9 Safety Edge:** The finished safety edge slope shall be planar forming a  $30^\circ \pm 5^\circ$  angle with the adjacent roadway surface and extend a minimum of five inches (5") below the roadway pavement's finished surface.

The safety edge shall be constructed with the top or final paving lift of a new pavement or overlay using a device that is mounted to or is a part of the screed portion of the laydown machine. The safety edge device shall be capable of constraining the asphalt concrete material to increase density of the extruded profile by reducing the volume. A conventional single strike-off plate is not acceptable. Compaction obtained from the extruded safety edge shall be acceptable when the extruded shape conforms to the specified shape.

During laydown operations if the extruded safety edge does not conform to the specified shape, the Contractor shall take immediate actions to correct the deficiency and to repair all non-compliant sections of safety edge. The Contractor shall stop paving operations until corrections to the laydown operation have been made and resumption of paving is approved by the Engineer or his designated representative.

321.8.10 Protection for Asphalt Base Course: Arterial roadway traffic shall not be allowed on a new asphalt base course that is less than five inches (5") in thickness without the written consent of the Engineer.

### 321.9 QUALITY CONTROL:

It is the contractor's responsibility to perform Quality Control monitoring and/or testing during asphalt concrete production to achieve the required compaction and to perform Quality Control monitoring and/or testing during asphalt concrete production to achieve the required mix properties. The Engineer may obtain samples of any portion of any material at any point of the operations for his own use. Also, the Engineer may order the use of any drying, proportioning and mixing equipment or the handling of any material discontinued which, in his/her opinion, fails to produce a satisfactory mixture.

The asphalt concrete produced shall conform to the requirements of the production tolerances established in section [321.10](#). When the asphalt concrete does not conform to the production tolerances, it shall be reported to the Engineer, and corrective quality control measures shall be implemented, or production shall cease immediately at no additional cost to the contracting Agency ~~or Engineer~~.

Requests for Referee Testing as described in 321.11 will only be considered based on quality control test results performed by a laboratory accredited by the AASHTO Accreditation Program (AAP) for the tests being performed or a laboratory listed in the current ADOT Directory of Approved Materials Testing Laboratories for the set of tests in question. The laboratory shall use properly certified technicians in accordance with ASTM D3666, Section 7 (Personnel Qualifications).

### 321.10 ACCEPTANCE:

**321.10.1 Acceptance Criteria:** ~~Unless otherwise specified, a~~ asphalt concrete will be divided into lots for the purpose of acceptance. A lot shall be ~~considered to be~~ one day's production. ~~When the quantity of asphalt concrete placed in a day exceeds 500 tons but is less than 2000 tons, the~~ Each lot shall be divided into ~~sublots of 500 ton sublots~~ or fraction thereof. ~~Where the quantity of asphalt concrete placed in a day exceeds 2000 tons, the day's production will be divided into four (4) approximately equal sublots. A minimum of one sample will be obtained from each lot.~~ Tests used to determine acceptance will be performed by ~~the Engineer or~~ a laboratory ~~employed by the Engineer. In either case the laboratory shall be~~ accredited by the AASHTO Accreditation Program (AAP), for the tests being performed. The contracting agency shall provide an appropriately accredited laboratory or laboratories to perform the acceptance testing. Laboratories shall use properly certified technicians in accordance with ASTM D3666, Section 7 (Personnel Qualifications). The acceptance laboratory will take representative samples of the asphalt concrete from each subplot to allow for testing of gradation, binder content, air voids, pavement thickness and compaction of base and surface courses. Acceptance of eEach subplot will be ~~accepted~~ based ~~up~~ upon the test data from the sample(s) from that subplot. All acceptance samples shall be taken using random locations

or times designated by the Engineer in accordance with ASTM D3665.

**321.10.2 Gradation, Binder Content and Air Voids:** The acceptance laboratory will take a sample of the asphalt concrete in accordance with the requirements of Section 2 or 4 of Arizona Test Methods 104 or AASHTO T-168 from each subplot. The minimum weight of the sample shall be 45 pounds. Asphalt binder content and gradation shall be determined in accordance with AASHTO T-308 using the ignition furnace for each subplot. The acceptance laboratory is responsible for obtaining the necessary materials and performing an ignition furnace calibration as outlined in AASHTO T-308 for each asphalt concrete mixture utilized on the project. The correction factor used for each test shall be clearly indicated on the report. The bulk density for Marshall Mix designs shall be tested in accordance with AASHTO T-245. The bulk density for Gyratory mix designs shall be determined in accordance with AASHTO T-312. The maximum theoretical density shall be determined in accordance with the requirements of AASHTO T-209 including fan drying per AASHTO T209 Section 15. Effective voids of the laboratory compacted specimens will be determined at a minimum of once per lot in accordance with the requirements of AASHTO T-269. Should the testing for effective air voids not meet the “Full Payment” or “No Corrective Action” requirements of Table [321-5](#), additional testing for laboratory air voids on the remaining sublots will be performed as necessary to determine the extent of the deficiency. Acceptance testing results will be furnished to the contractor and the supplier within five working days of receipt of samples by the acceptance laboratory.

During production, the allowable deviations from the mix design gradation targets are listed in the tables below. The allowable production tolerances may fall outside of the mix design gradation bands.

| <b>TABLE 321-3A</b>                                   |              |              |              |          |
|---|--------------|--------------|--------------|----------|
| <b>GRADATION ACCEPTANCE LIMITS FOR MARSHALL MIXES</b> |              |              |              |          |
| Sieve Size  | 3/8 inch Mix | 1/2 inch Mix | 3/4 inch Mix | Base Mix |
| 1 inch  | ---          | ---          | ---          | ±7%      |
| 3/4 inch  | ---          | ---          | ±7%          | ±6%      |
| 1/2 inch  | ---          | ±7%          | ---          | ---      |
| 3/8 inch  | ±7%          | ±6%          | ±6%          | ±6%      |
| No. 8   | ±6%          | ±6%          | ±6%          | ±6%      |
| No. 40  | ±4%          | ±4%          | ±4%          | ±4%      |
| No. 200   | ±2%          | ±2%          | ±2%          | ±2%      |

| <b>TABLE 321-3B</b>                                   |              |              |              |
|---|--------------|--------------|--------------|
| <b>GRADATION ACCEPTANCE LIMITS FOR GYRATORY MIXES</b> |              |              |              |
| Sieve Size  | 3/8 inch Mix | 1/2 inch Mix | 3/4 inch Mix |
| 3/4 inch  | ---          | ---          | ±7%          |
| 1/2 inch  | ---          | ±7%          | ±6%          |
| 3/8 inch  | ±7%          | ±6%          | ---          |
| No. 8   | ±6%          | ±6%          | ±6%          |
| No. 40  | ±4%          | ±4%          | ±4%          |
| No. 200   | ±2%          | ±2%          | ±2%          |

If the results from a single acceptance sample fall outside of the acceptance limits in Table [321-3A](#) or [321-3B](#) as applicable, a second sample shall be taken and if the second acceptance sample is also outside of the acceptance limits the Contractor shall cease production of asphalt concrete. Production shall not begin again until calibration test results verify that adjustments made to materials or proportions yield a gradation that falls within acceptance limits in Table [321-3A](#) or [321-3B](#) as applicable.

If the asphalt binder content is within ± 0.40% of the mix design target value, the asphalt concrete will be paid for at the contract unit price. If the asphalt binder content deviates by more than ± 0.40% from the mix design target value, the deficient area will be evaluated within the subplot by coring at maximum intervals of 100 feet from the deficient

sample. The asphalt content of the original deficient sample will be averaged with the asphalt binder content of the cores taken for re-evaluation to determine compliance with the acceptance requirements. If the resulting average of the asphalt binder content deviates by more than  $\pm 0.40\%$  from the mix design target value, then Table [321-4](#) shall apply to the subplot. Additional cores may be required to define the limits of the deficient area, and shall not be used for re-evaluating acceptance.

| <b>TABLE 321-4</b>                                     |  |   |
|--|--|---|
| <b>ASPHALT BINDER CONTENT ACCEPTANCE AND PENALTIES</b> |  |   |
|  | When the contracting agency is the owner:<br>Payment Reduction<br>(\$ per ton of asphalt concrete) | When the contracting agency is not the owner (i.e. permits):<br>Corrective Action |
| Deviation from that permitted                          |  |   |
| Over 0.2% <u>above</u> that permitted                  | Removal* or EA   | Removal* or EA  |
| Over 0.1% to 0.2% <u>above</u> that permitted          | \$6.00   | EA  |
| Over 0.0% to 0.1% <u>above</u> that permitted          | \$2.00   | EA  |
| Within permitted range                                 | Full Payment   | No Corrective Action  |
| Over 0.0% to 0.1% <u>below</u> that permitted          | \$2.00   | EA  |
| Over 0.1% to 0.2% <u>below</u> that permitted          | \$6.00   | EA  |
| Over 0.2% <u>below</u> that permitted                  | Removal* or EA   | Removal* or EA  |

NOTES: \*The Contractor shall remove and replace the entire subplot that is deficient.

EA = Engineering Analysis per Section 321.10.6

If the laboratory air voids fall within a range of 2.8% to 6.2%, the asphalt concrete will be paid for at the contract unit price. If the laboratory air voids are outside of this range, the deficient area will be evaluated within the subplot by coring at maximum intervals of 100 feet from the deficient sample. The laboratory air voids of the original deficient sample will be averaged with the laboratory air voids obtained from each of the cores taken for re-evaluation to determine compliance with the acceptance requirements. If the resulting average of the laboratory air voids is outside the indicated range, then Table [321-5](#) shall apply to the subplot. Additional cores may be required to define the limits of the deficient area, and shall not be used for re-evaluating acceptance.

| TABLE 321-5<br>LABORATORY VOIDS ACCEPTANCE AND PENALTIES               |  |   |
|--|--|---|
| Laboratory Air Voids (Measured at $N_{des}$ or 75 blows as applicable) | When the contracting agency is the owner:<br>Payment Reduction<br>(\$ per ton of asphalt concrete) | When the contracting agency is not the owner (i.e. permits):<br>Corrective Action |
| Less than 1.5%   | Removal* or EA   | Removal* or EA  |
| 1.5-2.0%   | \$5.00   | EA  |
| 2.1-2.7%   | \$2.00   | EA  |
| 2.8-6.2%   | Full Payment   | No Corrective Action  |
| 6.3-6.9%   | \$2.00   | EA  |
| 7.0-8.0%   | \$5.00   | EA  |
| Greater than 8.0%  | Removal* or EA   | Removal* or EA  |

NOTES: \*The Contractor shall remove and replace the entire subplot that is deficient

EA = Engineering Analysis per Section [321.10.6](#)

Removal for In-place Air Voids Greater than 11.0% is not eligible for Section [321.10.6](#).

If an agency or Engineer is purchasing asphalt concrete directly from a commercial material supplier, the agency or Engineer will use Section [321.10](#), and specifically Tables [321-3A](#) or [321-3B](#) as applicable, [321-4](#) and [321-5](#) from Section [321.10](#), when determining the acceptance of the asphalt concrete with the material supplier.

**321.10.3 Surface Testing:** If directed by the Engineer surface drainage test shall be performed. The completed surfacing shall be thoroughly compacted, smooth and true to grade and cross-section and free from ruts, humps, depressions or irregularities. An acceptable surface shall not vary more than 1/4 inch from the lower edge of a 12-foot straightedge when the straightedge is placed parallel to the centerline of the roadway. The straightedge shall be furnished by the contractor and shall be acceptable to the Engineer.

All streets shall be water tested for drainage in the presence of the Engineer or designated representative before final acceptance. Any areas not draining properly shall be corrected to the Engineer's satisfaction at the Contractor's expense. Water for this testing shall be provided and paid for by the Contractor.

When deviations in excess of the above tolerance are found, humps or depressions shall be corrected to meet the specified tolerance, or shall be cut out along neat straight lines and replaced with fresh hot mixture and thoroughly compacted to conform with and bond to the surrounding area. Materials and work necessary to correct such deviations shall be at no additional cost to the Contracting Agency.

**321.10.4 Asphalt Pavement Thickness:** Asphalt Pavement thickness will be determined from cores secured from each lift of each subplot ~~for this purpose~~. Such cores will be taken and measured by the Asphalt Concrete Coring Method. This method can be found ~~at~~ in Section [321.14](#). Each core location will be patched by the party responsible for the testing.

Acceptance or assessment of penalties for asphalt pavement thickness will be based on the combined total thickness of all asphalt concrete layers omitting all layers of asphalt-rubber asphalt concrete. If the final total pavement thickness exclusive of all ARAC layers is deficient from the target thickness by 0.25 inches or less, it will be paid for at the contract unit price.

If the pavement thickness deficiency is greater than 0.25 inches and the contracting agency is not the owner (i.e. permits) the following steps will apply:

- (1) If the thickness deficiency of the pavement exceeds 0.25 inch, the limits of the deficient area will be evaluated by coring at maximum intervals of 100 feet from the deficient core. The thicknesses of the original deficient core will be averaged with the thicknesses of the cores taken from 100 feet on each side of it to determine compliance with the acceptance requirements. If the resulting average thickness deficiency is greater than 0.25 inch, additional cores may be required to define the limits of the deficient area, and shall not be used

for re-evaluating acceptance.

(2) If the pavement thickness from step one above deviates from the target thickness by more than 0.25 inch but not more than 0.50 inch, corrective action will be required. This corrective action will consist of application of a Type II slurry seal coat in accordance to Section 715. The Contractor may present an engineering analysis outlining other proposed remedial measures for the consideration of the Engineer. The Engineer will review the engineering analysis and decide within 30 working days whether to accept the proposed remedial measures.

(3) If the pavement thickness from step one above deviates from the target thickness by more than 0.50 inch, corrective action will be required. The deficient area ~~will~~ shall be overlaid with no less than a 1 inch thick lift, for the full width of the pavement to meet or exceed the designed thickness, with ~~the~~ appropriate end and edge milling, with a mixture approved by the Engineer. The Contractor may present an engineering analysis outlining other proposed remedial measures for the Engineer's consideration. The Engineer will review the engineering analysis and decide within 10 working days whether to accept the proposed remedial measures. If the Engineer chooses to reject the engineering analysis, the indicated overlay will be constructed by the Contractor at no additional cost to the Owner.

If the Contracting Agency is the owner and the pavement thickness deficiency is greater than 0.25 inches but less than 0.50 inches and the contracting agency is the owner, Table 321-6 will apply. If the pavement thickness deficiency is greater than 0.5 inches the deficient area shall be overlaid with no less than a 1-inch thick lift for the full width of the pavement to meet or exceed the designed thickness using an asphalt mixture approved by the Engineer. The Contractor shall provide appropriate end and edge milling. The overlay and milling shall be accomplished by the Contractor at no additional cost to the Contracting Agency.

| <b>TABLE 321-6</b>  |   |
|---|---|
| <b>ASPHALT PAVEMENT THICKNESS PAYMENT REDUCTION</b>                                 |   |
| <b>For Thickness Deficiency of More Than 0.25 inches and less than 0.50 inches</b>  |   |
| <b><u>Total Specified Asphalt Pavement Thickness exclusive of ARAC (if any)</u></b> | <b><u>Reduction in Payment or Corrective Action applied to asphalt concrete except ARAC layers (if any)</u></b> |
| Less than 1.5 inches  | 50%   |
| 1.50 inches to 1.99 inches  | 33%   |
| 2.00 inches to 2.49 inches  | 25%   |
| 2.50 inches to 2.99 inches  | 20%   |
| 3.00 inches and over  | 17%   |

### **321.10.5 Density:**

#### **321.10.5.1 Pavement 1-1/2 Inches or Less in Nominal Thickness:**

Compaction shall consist of a "Rolling Method Procedure" using an established sequence of coverage with specified types of compactors. A pass shall be defined as one movement of a compactor in either direction. Coverage shall be the number of passes as are necessary to cover the entire width being paved.

The rolling sequence, the type of compactor to be used, and the number of coverages required shall be as shown in Table 321-7.

| TABLE 321-7  |                   |                 |                  |              |
|--|-------------------|-----------------|------------------|--------------|
| ROLLING SEQUENCE FOR LIFT THICKNESS 1½" OR LESS                    |                   |                 |                  |              |
| Rolling Sequence   | Type of Compactor |                 | No. of Coverages |              |
|  | Option No. 1      | Option No. 2    | Option No. 1     | Option No. 2 |
| Initial  | Static Steel      | Vibrating Steel | 1                | 1            |
| Intermediate   | Pneumatic Tired   | Vibrating Steel | 4                | 2- 4*        |
| Finish   | Static Steel      | Static Steel    | 1-3              | 1-3          |
| * Based on the roller pattern which exhibits the best performance. |                   |                 |                  |              |

The Contractor shall select the option for compaction and, when pneumatic-tired compactors are used will designate the tire pressure. Steel wheel compactors shall not be used in the vibratory mode for courses of one inch or less in thickness nor when the temperature of the asphaltic concrete falls below 180 degree F. Initial and intermediate compaction shall be accomplished before the temperature of the asphaltic concrete falls below 200 degree F.

Compaction will be deemed to be acceptable on the condition that the asphaltic concrete is compacted using the type of compactors specified, ballasted and operated as specified, and with the number of coverages of the compactors as specified.

### 321.10.5.2 Pavement Greater than 1-1/2 Inches in Nominal Thickness:

Achieving the required compaction is the responsibility of the contractor. The number and types of rollers is the contractor's responsibility and shall be sufficient to meet these requirements.

In-place air voids shall be determined in accordance with AASHTO T-269 utilizing cores taken from the finished pavement. The maximum theoretical density used in the determination of in-place air voids will be the average value from the acceptance samples determined for the Lot as outlined in [321.10.1](#).

The Engineer will designate one random test location for each subplot and the acceptance laboratory will obtain one core from that location. Regardless of subplot quantities or boundaries, a minimum of one core will be obtained per residential street and a minimum of one core per travel lane for collector and arterial streets. The outside one foot of each pass of the pavement course or any unconfined edge will be excluded from testing. The Engineer may exclude areas from the compaction lot that are not accessible by normal compaction equipment.

The Contractor will provide the traffic control to facilitate any coring operations necessary for compaction acceptance.

Cores will be taken per the Asphalt Concrete Coring Method. This method can be found in Section [321.14](#). Acceptance testing results will be furnished to the contractor within five working days of receipt of samples by the acceptance laboratory.

If the pavement density has in-place voids of 8.0% or less, the asphalt concrete will be paid for at the contract unit price. If the pavement density has in-place voids greater than 8.0%, the deficient area will be evaluated within the subplot by coring at maximum intervals of 100 feet from the deficient core(s). If both cores in a subplot are deficient, 3 to 4 additional cores may be necessary to re-evaluate acceptance. The in-place voids of all the original core(s), whether deficient or acceptable, will be averaged with the in-place voids of the cores taken for re-evaluation to determine compliance with the acceptance requirements. If the average of the in-place voids is greater than 8.0% then Table [321-8](#) shall apply to the subplot. Additional cores may be required to define the limits of the deficient area, and shall not be used for re-evaluating acceptance.

| TABLE 321-8   |  |   |
|---|--|---|
| PAVEMENT DENSITY PENALTIES  |  |   |
| Limits of In-place Air Voids for design lift thicknesses 1.5 inches and greater | When the contracting agency is the owner:<br><br>Payment Reduction<br>(\$ per ton of asphalt concrete) | When the contracting agency is not the owner (i.e. permits):<br><br>Corrective Action |
| Below 3.0%  | Removal* or EA   | Removal* or EA  |
| 3.0% to below 4.0%  | \$10.00  | EA and Type II Surry Seal   |
| 4.0% to 8.0%  | Full Payment   | No Corrective Action  |
| Greater than 8.0% to less than 9.0%   | \$6.00   | EA  |
| 9.0% to 10.0%   | \$10.00  | EA and Type II Surry Seal   |
| Greater than 10.0%  | Removal* or EA   | Removal* or EA  |

NOTES: \*The Contractor shall remove and replace the entire subplot that is deficient.

EA = Engineering Analysis per Section [321.10.6](#)

Removal for In-place Air Voids greater than 11.0% is not eligible for Section [321.10.6](#).

**321.10.6 Engineering Analysis (EA):** Within 10 working days after receiving notice that a lot or subplot of asphalt concrete is deficient and is found to fall within the “Removal or EA” band per Table(s) [321-4](#), [321-5](#), and/or [321-8](#) the contractor may submit a written proposal (Engineering Analysis) to accept the material in place at the applicable penalties along with possible remediation(s) listed in the “Removal or EA” category. Engineering Analysis can also be proposed for non-removal categories of “Corrective actions” when the contracting agency is not the owner (i.e. permits).

The Engineering Analysis shall contain an analysis of the anticipated performance of the asphalt concrete if left in place. The Engineering Analysis shall also detail the effect of any proposed corrective action to the material(s) in place as it relates to the in-place material’s performance. The Engineering Analysis shall be performed by a professional engineer experienced in asphalt concrete testing and mix designs.

If ~~the a~~ lot or subplot is ~~submitted-accepted~~ for referee testing ~~by and the referee test results still show a deficiency,~~ the contractor ~~shall have the~~ ten working days ~~allowed to prepare-submit~~ an engineering ~~analysis will-beginning~~ upon notification of referee test results.

When an Engineering Analysis recommends that a specific lot or subplot should not be removed, the Engineering Analysis will recommend that the following penalties (Table [321-9](#)) be paid when the contracting agency is the owner, for the specific criteria being reviewed by the EA.



| TABLE 321-9   |  |   |
|---|--|---|
| ENGINEERING ANALYSIS PENALTIES for REMOVAL* LOTS/SUBLOTS LEFT IN-PLACE        |  |   |
| Acceptance Criteria   | Acceptance Limits  | Penalty When Contracting Agency is the Owner (\$/Ton) |
| Asphalt Binder Content  | Over 0.2% points from that Permitted   | \$9.00  |
| Laboratory Air Voids (Measured at N <sub>des</sub> or 75 blows as applicable) | Less than 1.5% or Greater Than 8.0%  | <del>\$3.75</del> <u>\$7.50</u>                       |
| Limits of In-place Air Voids  | <del>Less than 10.0% to 11.0%</del><br><u>Less than 3% or Greater than 10.1%</u> | <del>\$15.00</del> <u>\$9.00</u>                      |

Within 15 working days, the Engineer will determine whether or not to accept the contractor's proposed Engineering Analysis.

### 321.11 REFEREE:

~~If the Contractor has reason to question the validity of any of the acceptance test results, the Contractor may request that the Engineer consider referee tests for final acceptance. In the event the contractor elects to question the acceptance test results for either asphalt binder content, laboratory air voids, density or a combination thereof for a subplot, the Contractor may make a written request for additional testing of that subplot. Any request for referee testing must describe the contractor's reasons for questioning the validity of the original acceptance test results and must clearly describe which set of acceptance tests are in question. The engineer may either accept or reject the request for referee testing. When referee testing is accepted, the Contractor (at the Contractors own expense) will engage an independent laboratory (at the Contractors own expense) who is accredited by the AAP or a laboratory listed in the current ADOT Directory of Approved Materials Testing Laboratories as appropriate in all of for the acceptance tests that are being questioned methods. The independent laboratory shall be The independent referee laboratory shall use properly certified technicians in accordance with ASTM D3666, Section 7 (Personnel Qualifications). acceptable to the Engineer and For the set of test results in question the referee laboratory shall perform a new set of acceptance tests (as required by Section 321.10 representing the area for the set of tests in question). The referee tests will replace the original acceptance tests that were in question. The results of these determinations will be binding on both the contractor and the agency.~~

These tests may include asphalt binder content, aggregate gradation, Marshall or Gyratory unit weight, maximum theoretical unit weight, laboratory air voids and in-place air voids (compaction). Samples for referee testing shall come from representative samples obtained from the completed pavement, as directed by the Engineer.

The number of samples taken will be the same as specified in Section 321.10. The independent laboratory shall compile the test results and transmit them to both the Engineer and the contractor. The independent laboratory shall include a report sealed and signed by an Engineer registered in the State of Arizona, who is experienced in asphalt concrete testing and mix design development. The signed report shall give an opinion that the material evaluated does or does not comply with project specifications, shall clearly describe any deficiencies, and the results will be binding between all parties.

### 321.12 MEASUREMENT:

Asphalt concrete pavement will be measured by the ton, or by the square yard, for the mixture actually used as allowed above, which shall include the required quantities of mineral aggregates, asphalt binder, and mineral admixture. Measurement shall include any tonnage used to construct intersections, roadways, streets, or other miscellaneous surfaces indicated on the plans or as directed by the Engineer.

### 321.13 PAYMENT:

The asphalt concrete measured as provided above will be paid for at the contract price per ton or square yard, as



adjusted per Section [321.10](#), which price shall be full compensation for the item complete, as herein described and specified.

Payment for tack coat will be by the ton diluted, based on the rate of application, as directed by the Engineer.

No payment will be made for any overrun in quantity of asphalt concrete in excess of 10 percent based on actual field measurement of area covered, design thickness, and the mix design unit weight. The calculations and payment for overrun will be by individual pay item. To compensate or adjust for a thickness deficiency in an underlying asphalt concrete course, the Engineer may authorize a quantity increase in excess of 10 percent for a subsequent asphalt concrete course. In such cases, the quantity in excess of 10 percent will be paid for at the lowest unit price.

Agency required repairs of existing pavement prior to roadway overlay operations will be paid for as a separate pay item.

Except as otherwise specified, no separate payment will be made for work necessary to construct miscellaneous items or surfaces of asphalt concrete.

#### **321.14 ASPHALT CORE METHOD: Core Drilling of Hot Mix Asphalt (HMA) for Specimens of 4" or 6" diameter**

**321.14.1 Scope:** This method is to establish a consistent method of the use of a diamond bit core to recover specimens of 4 or 6 inch diameter for laboratory analysis and testing. The method will require the use of: water, ice (bagged or other suitable type), dry ice, and a water-soap solution to be utilized when coring asphalt rubber concrete. Individuals doing the specimen recovery should be observing all safety regulations from the equipment manufacturer as well as the required job site safety requirements for actions, and required personal protective equipment.

**321.14.2 Core Drilling Device:** The core drilling device will be powered by an electrical motor, or by an acceptable gasoline engine. Either device used shall be capable of applying enough effective rotational velocity to secure a drilled specimen. The specimen shall be cored perpendicularly to the surface of pavement, and that the sides of the core are cut in a manner to minimize sample distortion or damage. The machinery utilized for the procedure shall be on a mounted base, have a geared column and carriage that will permit the application of variable pressure to the core head and carriage throughout the entire drilling operation. The carriage and column apparatus shall be securely attached to the base of the apparatus; and the base will be secured with a mechanical fastener or held in place by the body weight of the operator. The core drilling apparatus shall be equipped with a water spindle to allow water to be introduced inside of the drill stem while operating. The cutting edge of the core drill bit shall be of hardened steel or other suitable material with embedded diamond chips in the cutting surface. The core barrel shall be of sufficient diameter to secure a specimen that is a minimum of four or six inches or whichever is prescribed for necessary testing. The core barrel shall not be missing more than one of the teeth used for cutting; if so it shall be discarded and another barrel shall be used. The core barrel shall also be a minimum of two inches longer than the anticipated depth of pavement in accordance with project paving plans.

**321.14.3 Accessory Equipment:** A sufficient supply of ice and dry ice shall be provided to sufficiently cool the pavement prior to securing the samples from the designated areas in the pavement. The ice should also be used to adjust the temperature of the water used to cool the core bit. A water supply (usually a plastic 35 – 55 gal drum) with sufficient hose to introduce the water into and through the spindle of the coring device by gravity feed. The drum should be white or light in color to minimize excessive thermal heating of the water (*for coring of asphalt rubber cores see Note 1*). At no time shall the water utilized in the coring operation exceed 65° F during the coring operation. Ice shall be utilized to ensure the temperature control of the water being introduced during the cutting operation. An ice chest or other suitably insulated container that can maintain a temperature of less than 70° F shall be used to secure the specimens during transport. The container will be equipped with flat shelving that will support the drilled cores throughout the entire specimen dimension during transport back to the testing facility.

Miscellaneous hand tools to remove the drilled specimen from the drill hole or the core barrel taking great care in not disturbing the specimen more than necessary (refer to fig. 1 in ASTM D5361-05).

**321.14.4 Process:** The pavement surface at the time of coring shall not exceed a temperature of 90° F; the pavement shall be conditioned with ice or dry ice to ensure that this requirement is met. Immediately after it has been ensured that the pavement has dropped to the required temperature, core drilling shall begin. The operator will then apply an even and continuous pressure (Note 2) to penetrate through the full depth of the pavement. The operator will concurrently ensure that enough water is moving over the core surface as to adequately remove any and all cuttings that could damage the drilled core. After the pavement thickness has been penetrated the core shall be carefully removed from either the drill hole or the core barrel and be immediately transferred to an ice chest or other suitable container. Each individual core shall be placed on a shelf in the cooler with the exposed side of the specimen facing down, or the “top side” down. If the specimen is a two lift core, the only acceptable means of separating lifts is with a power or other acceptable wet saw type of equipment (conforming to ASTM D5361-05); however, at no time shall cores be split using a mallet and screwdriver or metal straight edge when being tested for bulk density. Perpendicularity of the specimen shall be checked in the field after the specimen has been extracted from the surface. The core operator shall hold the core up to eye level and place the core top side down in a “speed square” or small carpenters square. The specimen placed in the square shall not depart from perpendicular to the axis more than 0.5° (approximately equivalent to 1/16 of an inch in 6 inches). If the specimen is outside of this distance from square it shall be discarded in the field and another sample cored that falls within tolerance. The cores upon arriving at the laboratory for testing shall be carefully cleaned and measured for thickness in accordance with ASTM D3549. A speed square shall be utilized to measure perpendicularity as compared to a 90° degree angle and shall not depart from perpendicular to the axis more than 0.5° (approximately equivalent to 1/16 of an inch in 6 inches). All remaining testing shall be done within the parameters of the current project and / or agency required specification.

~~*-End of Section-*~~

\*Note 1 – It should be noted that when the material to be cored is a rubberized asphalt mixture a wetting agent such as liquid dish soap shall be added to the water barrel to hinder the material from sticking or allowing the binder to spread during coring.

\*Note 2 – This refers to pressure exerted on the core barrel and machine during the coring process. Too much pressure can cause damage to the core barrel and the motor; and too little pressure can cause a glazing of the diamonds, reducing cutting efficiency and premature wear of the barrel

~~*-End of Section -*~~

**PLACEMENT AND CONSTRUCTION OF ASPHALT CONCRETE PAVEMENT****321.1 DESCRIPTION:**

This section is to provide specifications for furnishing all materials, mixing at a plant, hauling and placing a mixture of aggregate materials, mineral admixture and asphalt binder to form a pavement course for placement upon a previously prepared base or sub base.

**321.2 MATERIALS AND MANUFACTURE:**

The materials shall conform to Section [710](#) for the type specified. The specific required mix type shall be called out in the contract documents or as directed by the Engineer.

**321.3 WEATHER AND MOISTURE CONDITIONS:**

Asphalt concrete shall be placed only when the surface is dry, and when the atmospheric temperature in the shade is 40 degrees F. (50 degrees F for Asphalt Concrete lift less than 2 inch thick) or above. No asphalt concrete shall be placed when the weather is foggy or rainy, or when the base or sub base on which the material is to be placed is unstable. Asphalt concrete shall be placed only when the Engineer determines that weather conditions are suitable.

**321.4 APPLICATION OF TACK COAT:**

A tack coat shall be applied to all existing and to each new course of asphalt concrete prior to the placing of a succeeding lift of asphalt concrete. The tack coat may be deleted when a succeeding layer of asphalt concrete is being applied over a freshly laid course that has been subjected to very little traffic when approved by the Engineer.

The application of the tack coat shall comply with Section [329](#). The grade of emulsified asphalt shall be SS-1h or CSS-1h as specified in Section [713](#).

The same material that is specified above for the tack coat shall be applied to the vertical surfaces of existing pavements, curbs, and gutters, against which asphalt concrete is to be placed.

The surface to be covered may require repair or patching as directed by the Engineer. This shall be addressed in the project specifications prior to the bidding of the project.

**321.5 MIX DESIGN**

The mix design shall be submitted to the Engineer at least five working days prior to the start of asphalt concrete production. Mix designs provided by the agency may be utilized on projects at the Engineer's discretion. The Engineer will review and approve the mix design to assure it contains all of the required information as outlined in Section [710.3.1](#). The target values for gradations, binder contents, and air voids will be established as the accepted Job Mix Formula (JMF) based upon the mix design. Mix designs not containing all of the information will be returned within five working days of receipt of all mix design information, for action and resubmission by the contractor.

Once the mix design has been approved by the agency and the mixing plant selected, the Contractor and/or his supplier shall not change plants nor utilize additional mixing plants without prior approval of the Engineer.

If the contractor elects to change its source of material, the contractor shall furnish the Engineer with a new mix design, which meets the requirements of Section [710](#), as amended by the Project Specifications.

The contractor may make self-directed target changes to the approved mix design within the limits shown below. Requests for self-directed target changes shall be made in writing and acknowledged by the Engineer prior to the start of production of a lot and will remain in effect until such time as any additional changes are implemented. The self-directed target changes must meet the contract requirements for mix design criteria and gradation limits.

| <b>TABLE 321-1</b>                            |  |
|---|--|
| <b>ALLOWABLE SELF-DIRECTED TARGET CHANGES</b> |  |
| MEASURED CHARACTERISTICS                      | ALLOWABLE SELF-DIRECTED TARGET CHANGES |
| Gradation (Sieve Size)                        |  |
| 3/8 inch                                      | ± 4% from mix design target value      |
| No 8  | ± 4% from mix design target value      |
| No 40   | ± 2% from mix design target value      |
| No 200  | +0.5% from mix design target value     |
| Binder Content                                | ± 0.2% from mix design target value    |
| Effective Air Voids                           | None                                   |

The contractor may propose target changes, other than self-directed changes, to the approved mix design for the approval of the Engineer. The Engineer will determine if the proposed target change will result in mix production that meets the contract requirements for mix design criteria and gradation limits. The target changes will not be retroactive for the purpose of acceptance.

### **321.6 MIX PRODUCTION:**

All materials shall be proportioned by weight in a hot mix asphalt plant in the proportions required by the mix design to provide a homogeneous and workable mass. Each hot mix asphalt plant shall be inspected in accordance with the provisions contained in the 'Hot Mix Asphalt Production Facilities' by the Arizona Rock Products Association and shall have a current inspection certificate. All measuring devices shall be calibrated at least annually by a technician licensed by the Arizona Bureau of Weights & Measures. Mixing plants shall conform to the requirements of AASHTO M-156, except as modified herein.

In drum mix plants the mineral admixture shall be added and thoroughly mixed with the mineral aggregate by means of a mechanical mixing device prior to the mineral aggregate and mineral admixture entering the dryer. The moisture content of the combined mineral aggregate shall be a minimum of three percent by weight of the aggregate during the mixing process.

For drum-mix plants, the mineral admixture shall be weighed across a weight belt, or other approved alternative weighing system, with a weight totalizer prior to entry into the mechanical mixing device. The mechanical mixing device shall be a pugmill type mixer that is in good working condition. The rate of the aggregate feed shall not exceed the mixing device's capacity in ton per hour. The mixer shall be constructed to minimize the loss of mineral admixture and shall be located in the aggregate delivery system at a location where the mixed material can be readily inspected. The mixing device shall be capable of effective mixing in the full range of the asphalt concrete production rates.

The hot plant and equipment shall be constructed and operated to prevent loss of mineral admixture through the dust collection system of the plant.

A positive signal system shall be provided and utilized during production whereby the mixing shall automatically be stopped if the mineral admixture is not introduced into the mineral aggregate. The plant will not be permitted to operate unless the signal system is in good working condition.

The introduction of bituminous material shall be controlled by an automated system fully integrated with the controls of the mineral aggregate and mineral admixture. The production of the plant shall be controlled by the rate required to obtain a uniform mixture of all components. Drying and heating shall be accomplished in such a manner as to preclude the mineral admixture from becoming coated with un-spent fuel. The completed asphalt concrete may be held in storage for up to 12 hours in insulated or heated silos, providing the minimum temperature noted herein for placement and compaction is met behind the placement device. If the Engineer determines that there is an excessive amount of heat, heat loss, drain down, segregation and/or oxidation of the mixture due to temporary storage, use of surge bins or storage bins will be discontinued.

The temperature of the asphalt concrete, with unmodified binders, upon discharge from the mixer shall not exceed 335 degrees F. The discharge temperature may be increased on the recommendation of the binder supplier, when approved by the Engineer. If the asphalt concrete is discharged from the mixer into a hopper, the hopper shall be constructed so that segregation of the asphalt concrete will be minimized.

### **321.7 TRANSPORTATION:**

Petroleum distillates or other substances that will have a detrimental effect on the asphalt concrete shall not be used as a release agent.

The beds of all transportation units shall be clean and smooth to allow the free flow of material into the paving machine's hopper.

Tarpaulins shall be furnished on all trucks and used when weather condition warrant, or if directed by the Engineer.

### **321.8 PLACEMENT:**

Placement of asphalt concrete pavement shall not commence until authorized by the Engineer. The Engineer's authorization to allow commencement of asphalt concrete paving will generally require all newly constructed valley gutters, curbing, and curb and gutters which new pavement is to be placed against to be in-place and in an acceptable condition. While it is preferred to have all newly constructed concrete items against which new pavement is to be placed be in an acceptable condition, the Engineer may allow paving to commence based on weather, the amount of defective concrete, or other considerations.

**321.8.1 Placing:** All courses of asphalt concrete shall be placed and finished by means of a self-propelled paving machine equipped with an automatically actuated control system, except under certain conditions or at locations where the Engineer deems the use of a self-propelled paving machine impracticable.

The control system shall control the elevation of the screed at each end by controlling the elevation of one end directly and the other end indirectly either through controlling the transverse slope or alternatively when directed, by controlling the elevation of each end independently.

The control system shall be capable of working with one of the following devices:

- (a) Ski or non-contact device of not less than 30 feet in length, supported throughout its entire length
- (b) Taut stringline or wire set to grade
- (c) Short ski or sonar sensing units from curb control
- (d) Joint matching shoe

Failure of the control system to function properly shall be cause for the suspension of asphalt concrete production. In order to achieve a continuous operation, the speed of the paving machine shall be coordinated with the hot mix plant and transport units.

If the asphalt concrete is dumped from the hauling vehicles directly into the paving machine, care shall be taken to avoid jarring the machine or moving it out of alignment. No vertical load shall be exerted on the paving machine by the truck.

If asphalt concrete is dumped upon the surface being paved and subsequently loaded in the paving machine, the loading equipment shall be self-supporting and shall not exert any vertical load on the paving machine. Substantially all of the asphalt concrete shall be picked up and loaded into the paving machine.

Self-propelled paving machines shall spread the mixture without segregation or tearing, true to line, grade and crown indicated on the Project plans. Pavers shall be equipped with hoppers and augers that will distribute the mixture uniformly in front of an adjustable floating screed. The raising of the hopper wings must be minimized and the paving machine will not be operated when in an empty condition.

Screeds shall include any strike-off device operated by tamping or vibrating action which is effective, without

tearing, shoving or gouging the mixture and which produces a course with a uniform texture and density for the full width being paved. Screeds shall be adjustable as to height and crown and shall be equipped with a controlled heating device for use when required. In the case of the screed, auger extensions and vibrators shall be installed wherever the screed is extended more than one (1) foot beyond the end of the base auger or auger extension. However, when placing material against an extremely uneven curb or edge over a short distance, the Engineer may waive the auger extensions and vibrators.

At any place not accessible to the roller, the mixture shall be thoroughly compacted with tampers to provide a uniform and smooth layer over the entire area compacted in this manner.

**321.8.2 Joints:** Transverse joints, before a surface course is placed in contact with a cold transverse construction joint, the cold existing asphalt concrete shall be trimmed to a vertical face for its full depth exposing a fresh face. The fresh face shall be tack coated prior to placement of the new asphalt concrete. After placement and finishing the new asphalt concrete, both sides of the joint shall be dense and the joint shall be smooth and tight. The surface in the area of the joint shall not deviate more than 1/4 inch from a 12-foot straightedge, when tested with the straightedge placed across the joint, parallel to the centerline.

Longitudinal joints of each asphalt course shall be staggered a minimum of 6 inches with relation to the longitudinal joint of the immediate underlying course's cold longitudinal construction joint.

Longitudinal joints with existing or cold (more than 32 hours old) asphalt concrete shall require the existing pavement to be trimmed to a vertical face for its full depth exposing a fresh face. The fresh face shall be tacked prior to placement of the adjacent course. Longitudinal joints with an existing asphalt pavement that is less than 32 hours old that has had its edge protected from damage may have adjacent new asphalt concrete placed after applying the required tack coat. After placement and finishing of longitudinal joints, both sides of the joint shall be dense and the joint shall be smooth and tight. The surface in the area of the joint shall not deviate more than 1/4 inch from a 12-foot straightedge, when tested with the straightedge placed across the joint in any direction.

**321.8.3 Asphalt Leveling Course:** A leveling course shall be used when specified, or as directed in writing by the Engineer, to bring existing pavement to a uniform grade prior to placing an overlay or other course. If a leveling course is being applied on an Asphalt surface, a tack coat shall be applied. The compaction requirements contained in Section [321.10](#) do not apply to leveling courses.

**321.8.4 Compaction; Asphalt Base Course and Surface Course:** It is the contractor's responsibility to perform Quality Control monitoring and/or testing during compaction operations to achieve the required compaction. The temperature of the asphalt concrete immediately behind the laydown machine shall meet the minimum requirements of Table [321-2](#). A probe type electronic thermometer with a current calibration sticker attached will be used to measure the temperature of the asphalt concrete mixture. When measuring the temperature of the mat, the probe shall be inserted at mid-depth and as horizontal as possible to the mat. The minimum temperatures in Table 321-2 do not guarantee that the asphalt mix will be compacted to the required density. The contractor is responsible to achieve the required compaction.

| <b>MINIMUM ASPHALT CONCRETE PLACEMENT TEMPERATURE</b> |                        |     |     |       |     |               |
|---|------------------------|-----|-----|-------|-----|---------------|
| Base <sup>(1)</sup> Temp (°F)                         | Mat Thickness (inches) |     |     |       |     |               |
|   | 1/2                    | 3/4 | 1   | 1 1/2 | 2   | 3 and greater |
| 40 – 50   | ---                    | --- | 310 | 300   | 285 | 275           |
| 50 – 60   | ---                    | 310 | 300 | 295   | 280 | 270           |
| 60 – 70   | 310                    | 300 | 290 | 285   | 275 | 265           |
| 70 – 80   | 300                    | 290 | 285 | 280   | 270 | 265           |
| 80 – 90   | 290                    | 280 | 270 | 270   | 265 | 260           |
| +90   | 280                    | 275 | 265 | 265   | 260 | 255           |

(1) Base on which mix is to be placed

Asphalt compaction equipment shall be of sufficient size and weight to accomplish the required compaction. All compaction equipment shall be operated and maintained in accordance with the manufacturer's recommendations and the project requirements. During the rolling operation, the speed of the roller shall not exceed 3 miles per hour, unless otherwise approved by the Engineer.

Pneumatic tired compactors shall be equipped with skirt-type devices mounted around the tires so that the temperature of the tires will be maintained during the compaction process.

The Engineer will determine the acceptability of the pavement compaction in accordance with Section [321.10](#).

**321.8.5 Smoothness:** The completed surfacing shall be thoroughly compacted, smooth and true to grade and cross-section and free from ruts, humps, depressions or irregularities. An acceptable surface shall not vary more than one-fourth ( $\frac{1}{4}$ ) inch from the lower edge of a 12-foot straightedge when the straightedge is placed parallel to the centerline of the roadway.

**321.8.6 Asphalt Concrete Overlay:** Asphalt concrete overlay consists of the placing and compacting plant mix asphalt concrete over existing pavement. The mix design and thickness of the overlay shall be as shown on the plans or as specified in the special provisions.

Except when the existing asphalt surface is to be preheated and remixed, pavement surfaces shall be prepared as follows:

- (a) Areas designated for pavement repair by the contract documents (which may include severely raveled areas, severely cracked areas, over-asphalted areas, and other defects) shall be cut out and replaced. Pavement repairs shall be completed and approved before placing asphalt concrete overlay.
- (b) Before placing asphalt concrete overlay, milling shall be done as shown on the plans or specified in the special provisions and shall be in accordance with Section [317](#).
- (c) After pavement repairs and milling have been completed the entire surface shall be cleaned with a power broom.
- (d) After surfaces have been prepared to the satisfaction of the Engineer, they shall receive a tack coat per Section [321.4](#). Traffic will not be permitted to travel over surfaces which have received a tack coat, except when tack coat is applied to milled surfaces in compliance with Section [317.2](#) for dust control purposes. When the overlay is to extend onto a concrete gutter, the gutter shall be thoroughly cleaned of loose dust and cement particles and shall be tack coated.

Asphalt concrete overlay shall be placed as specified in Section [321.8.1](#) and compacted as specified in Section [321.8.4](#). The surface smoothness shall meet the tolerances specified in Section [321.8.5](#).

Frames and covers of manholes, survey monuments, valve boxes, clean-outs and other existing structures shall be adjusted in accordance with Section [345](#) to set flush with the finished surface of the new pavement. During adjustment if pavement or base materials are removed or disturbed, they shall be replaced with approved materials installed in a manner acceptable to the Engineer.

On roads without curb and gutter, the existing unpaved shoulder elevation shall be adjusted by the Contractor to match the elevation at the edge of the new overlay and slope away from the new pavement surface at a rate that the existing quantity of shoulder material will allow. Shoulder material shall be compacted to a minimum of 95% of maximum density, determined in accordance with Section [301.3](#). Shoulder adjustment to match the new pavement surface elevation shall not be measured. The cost of shoulder adjustment shall be included in the price paid for the asphalt concrete overlay or other related pay items. When the Engineer determines an insufficient amount of material is available for shoulder adjustment, the Engineer may require the Contractor to provide additional material. Acceptable material for shoulders includes the existing shoulder material, millings, untreated base materials, or a granular material approved by the Engineer. Engineer requested imported material for shoulder adjustment is not included in the price paid for the asphalt concrete overlay.



**321.8.7 Pavement Fabric Interlayer:** Pavement fabric interlayer shall be used only when specified on the plans or in the specifications.

Pavement fabric interlayer shall be in accordance with Table [796-1](#) and be the class designated on the plans or in the specifications.

Asphalt binder coat used to bond the fabric to the pavement shall be paving asphalt PG 70-10 asphalt cement conforming to the requirements of Section [711](#). The application and distributing equipment for the asphalt binder shall conform to the requirements of Section [330](#). The asphalt binder coat shall be uniformly spray applied to the prepared pavement surface at the rate of 0.20 gallons per square yard for Class B fabric or at the rate of 0.25 gallons per square yard for Class A fabric. Some underlying surfaces may require a higher or lower application rate. A test strip may be necessary to determine the proper application rate. The width of liquid asphalt cement application shall be the fabric width, plus six inches.

Neither the asphalt binder coat or fabric interlayer shall be placed when weather conditions, in the opinion of the Engineer, are not suitable. The asphalt binder and fabric interlayer shall only be placed when the pavement is dry, the ambient air temperature is 50 degrees F and rising, and pavement temperature is 40 degrees F and rising.

Equipment for placing the fabric shall be mechanized and capable of handling full rolls of fabric. The equipment shall be able to lay the fabric smoothly to maximize pavement contact and remove air bubbles. Stiff bristle brooms shall be used to smooth the fabric. The equipment used to place the fabric shall be in good working order and is subject to approval by the Engineer.

Pavement fabric interlayer shall not be placed if the in-place binder is hotter than 325 degrees F or has cooled to 180 degrees F or below (as determined by non-contact thermometer).

Pavement fabric interlayer shall be placed onto the asphaltic binder with the heat bonded side up with a minimum amount of wrinkling or folding. Remaining wrinkles or folds 1-inch and larger shall be removed or slit and shingle-lapped in the direction of paving. Burning or torching of wrinkles is not allowed. Fabric shall overlap three to six inches to insure full closure of the joint. Transverse joints shall be shingle-lapped in the direction of paving to prevent edge pickup by the paver. A second application of hand-placed asphalt binder may be required at laps and repairs as determined by the Engineer to ensure proper binding of the narrow double fabric layer.

All areas where fabric has been placed shall be paved with asphaltic concrete during the same workshift. Placement of the asphaltic concrete shall closely follow fabric lay down. The temperature of the asphaltic concrete immediately behind the laydown machine shall not exceed 325 degrees F. In the event that the asphalt binder coat bleeds through the fabric causing construction problems before the overlay is placed, the affected areas shall be sanded with a sand blotter in compliance with Section [333](#). Excess sand shall be removed before beginning the paving operation. In the event of rainfall prior to the placement of the asphaltic concrete, the fabric shall be allowed to dry before the asphalt concrete is placed.

Turning of the paving machine or of other vehicles on the fabric shall be gradual and kept to a minimum to avoid damage to the fabric. Should equipment tires stick to the fabric during pavement operations, small quantities of paving asphalt concrete shall be broadcast on the fabric to prevent pick-up. Decrease of binder rate in order to minimize pick-up on tires is not allowed.

**321.8.8 Thickened Edge:** When the depth of the thickened edge extends four inches or more below the bottom of the asphalt pavement, the portion of the thickened edge extending below the asphalt pavement shall be placed and compacted prior to placement of the asphalt pavement. Placement of tack coat on the surface of the compacted thickened edge asphalt may be omitted when additional asphalt pavement is placed on the same day and the Engineer agrees that the surface of the thickened edge asphalt has remained clean.

When the depth of the thickened edge extends less than four inches below the bottom of the asphalt pavement, the portion below the asphalt pavement may be placed and compacted with the asphalt pavement in a single operation.



**321.8.9 Safety Edge:** The finished safety edge slope shall be planar forming a  $30^{\circ} \pm 5^{\circ}$  angle with the adjacent roadway surface and extend a minimum of five inches (5") below the roadway pavement's finished surface.

The safety edge shall be constructed with the top or final paving lift of a new pavement or overlay using a device that is mounted to or is a part of the screed portion of the laydown machine. The safety edge device shall be capable of constraining the asphalt concrete material to increase density of the extruded profile by reducing the volume. A conventional single strike-off plate is not acceptable. Compaction obtained from the extruded safety edge shall be acceptable when the extruded shape conforms to the specified shape.

During laydown operations if the extruded safety edge does not conform to the specified shape, the Contractor shall take immediate actions to correct the deficiency and to repair all non-compliant sections of safety edge. The Contractor shall stop paving operations until corrections to the laydown operation have been made and resumption of paving is approved by the Engineer or his designated representative.

**321.8.10 Protection for Asphalt Base Course:** Arterial roadway traffic shall not be allowed on a new asphalt base course that is less than five inches (5") in thickness without the written consent of the Engineer.

### **321.9 QUALITY CONTROL:**

It is the contractor's responsibility to perform Quality Control monitoring and/or testing during asphalt concrete production to achieve the required compaction and to perform Quality Control monitoring and/or testing during asphalt concrete production to achieve the required mix properties. The Engineer may obtain samples of any portion of any material at any point of the operations for his own use. Also, the Engineer may order the use of any drying, proportioning and mixing equipment or the handling of any material discontinued which, in his/her opinion, fails to produce a satisfactory mixture.

The asphalt concrete produced shall conform to the requirements of the production tolerances established in section [321.10](#). When the asphalt concrete does not conform to the production tolerances, it shall be reported to the Engineer, and corrective quality control measures shall be implemented, or production shall cease immediately at no additional cost to the contracting Agency.

Requests for Referee Testing as described in 321.11 will only be considered based on quality control test results performed by a laboratory accredited by the AASHTO Accreditation Program (AAP) for the tests being performed or a laboratory listed in the current ADOT Directory of Approved Materials Testing Laboratories for the set of tests in question. The laboratory shall use properly certified technicians in accordance with ASTM D3666, Section 7 (Personnel Qualifications).

### **321.10 ACCEPTANCE:**

**321.10.1 Acceptance Criteria:** Asphalt concrete will be divided into lots for the purpose of acceptance. A lot shall be one day's production. Each lot shall be divided into sublots of 500 ton or fraction thereof. Tests used to determine acceptance will be performed by a laboratory accredited by the AASHTO Accreditation Program (AAP) for the tests being performed. The contracting agency shall provide an appropriately accredited laboratory or laboratories to perform the acceptance testing. Laboratories shall use properly certified technicians in accordance with ASTM D3666, Section 7 (Personnel Qualifications). The acceptance laboratory will take representative samples of the asphalt concrete from each subplot to allow for testing of gradation, binder content, air voids, pavement thickness and compaction of base and surface courses. Acceptance of each subplot will be based on the test data from the sample(s) from that subplot. All acceptance samples shall be taken using random locations or times designated by the Engineer in accordance with ASTM D3665.

**321.10.2 Gradation, Binder Content and Air Voids:** The acceptance laboratory will take a sample of the asphalt concrete in accordance with the requirements of Section 2 or 4 of Arizona Test Methods 104 or AASHTO T-168 from each subplot. The minimum weight of the sample shall be 45 pounds. Asphalt binder content and gradation shall be determined in accordance with AASHTO T-308 using the ignition furnace for each subplot. The acceptance laboratory is responsible for obtaining the necessary materials and performing an ignition furnace calibration as outlined in AASHTO T-308 for each asphalt concrete mixture utilized on the project. The correction factor used for

each test shall be clearly indicated on the report. The bulk density for Marshall Mix designs shall be tested in accordance with AASHTO T-245. The bulk density for Gyratory mix designs shall be determined in accordance with AASHTO T-312. The maximum theoretical density shall be determined in accordance with the requirements of AASHTO T-209 including fan drying per AASHTO T209 Section 15. Effective voids of the laboratory compacted specimens will be determined at a minimum of once per lot in accordance with the requirements of AASHTO T-269. Should the testing for effective air voids not meet the "Full Payment" or "No Corrective Action" requirements of Table [321-5](#), additional testing for laboratory air voids on the remaining sublots will be performed as necessary to determine the extent of the deficiency. Acceptance testing results will be furnished to the contractor and the supplier within five working days of receipt of samples by the acceptance laboratory.

During production, the allowable deviations from the mix design gradation targets are listed in the tables below. The allowable production tolerances may fall outside of the mix design gradation bands.

| <b>TABLE 321-3A</b>                                   |              |              |              |          |
|---|--------------|--------------|--------------|----------|
| <b>GRADATION ACCEPTANCE LIMITS FOR MARSHALL MIXES</b> |              |              |              |          |
| Sieve Size  | 3/8 inch Mix | 1/2 inch Mix | 3/4 inch Mix | Base Mix |
| 1 inch  | ---          | ---          | ---          | ±7%      |
| 3/4 inch  | ---          | ---          | ±7%          | ±6%      |
| 1/2 inch  | ---          | ±7%          | ---          | ---      |
| 3/8 inch  | ±7%          | ±6%          | ±6%          | ±6%      |
| No. 8   | ±6%          | ±6%          | ±6%          | ±6%      |
| No. 40  | ±4%          | ±4%          | ±4%          | ±4%      |
| No. 200   | ±2%          | ±2%          | ±2%          | ±2%      |

| <b>TABLE 321-3B</b>                                   |              |              |              |
|---|--------------|--------------|--------------|
| <b>GRADATION ACCEPTANCE LIMITS FOR GYRATORY MIXES</b> |              |              |              |
| Sieve Size  | 3/8 inch Mix | 1/2 inch Mix | 3/4 inch Mix |
| 3/4 inch  | ---          | ---          | ±7%          |
| 1/2 inch  | ---          | ±7%          | ±6%          |
| 3/8 inch  | ±7%          | ±6%          | ---          |
| No. 8   | ±6%          | ±6%          | ±6%          |
| No. 40  | ±4%          | ±4%          | ±4%          |
| No. 200   | ±2%          | ±2%          | ±2%          |

If the results from a single acceptance sample fall outside of the acceptance limits in Table [321-3A](#) or [321-3B](#) as applicable, a second sample shall be taken and if the second acceptance sample is also outside of the acceptance limits the Contractor shall cease production of asphalt concrete. Production shall not begin again until calibration test results verify that adjustments made to materials or proportions yield a gradation that falls within acceptance limits in Table [321-3A](#) or [321-3B](#) as applicable.

If the asphalt binder content is within  $\pm 0.40\%$  of the mix design target value, the asphalt concrete will be paid for at the contract unit price. If the asphalt binder content deviates by more than  $\pm 0.40\%$  from the mix design target value, the deficient area will be evaluated within the subplot by coring at maximum intervals of 100 feet from the deficient sample. The asphalt content of the original deficient sample will be averaged with the asphalt binder content of the cores taken for re-evaluation to determine compliance with the acceptance requirements. If the resulting average of the asphalt binder content deviates by more than  $\pm 0.40\%$  from the mix design target value, then Table [321-4](#) shall apply to the subplot. Additional cores may be required to define the limits of the deficient area, and shall not be used for re-evaluating acceptance.

| <b>TABLE 321-4</b>                                     |  |   |
|--|--|---|
| <b>ASPHALT BINDER CONTENT ACCEPTANCE AND PENALTIES</b> |  |   |
| Deviation from that permitted                          | When the contracting agency is the owner:<br>Payment Reduction<br>(\$ per ton of asphalt concrete) | When the contracting agency is not the owner (i.e. permits):<br>Corrective Action |
| Over 0.2% <u>above</u> that permitted                  | Removal* or EA   | Removal* or EA  |
| Over 0.1% to 0.2% <u>above</u> that permitted          | \$6.00   | EA  |
| Over 0.0% to 0.1% <u>above</u> that permitted          | \$2.00   | EA  |
| Within permitted range                                 | Full Payment   | No Corrective Action  |
| Over 0.0% to 0.1% <u>below</u> that permitted          | \$2.00   | EA  |
| Over 0.1% to 0.2% <u>below</u> that permitted          | \$6.00   | EA  |
| Over 0.2% <u>below</u> that permitted                  | Removal* or EA   | Removal* or EA  |

NOTES: \*The Contractor shall remove and replace the entire subplot that is deficient.  
EA = Engineering Analysis per Section 321.10.6

If the laboratory air voids fall within a range of 2.8% to 6.2%, the asphalt concrete will be paid for at the contract unit price. If the laboratory air voids are outside of this range, the deficient area will be evaluated within the subplot by coring at maximum intervals of 100 feet from the deficient sample. The laboratory air voids of the original deficient sample will be averaged with the laboratory air voids obtained from each of the cores taken for re-evaluation to determine compliance with the acceptance requirements. If the resulting average of the laboratory air voids is outside the indicated range, then Table 321-5 shall apply to the subplot. Additional cores may be required to define the limits of the deficient area, and shall not be used for re-evaluating acceptance.

| <b>TABLE 321-5</b>  |  |   |
|---|--|---|
| <b>LABORATORY VOIDS ACCEPTANCE AND PENALTIES</b>                              |  |   |
| Laboratory Air Voids (Measured at N <sub>des</sub> or 75 blows as applicable) | When the contracting agency is the owner:<br>Payment Reduction<br>(\$ per ton of asphalt concrete) | When the contracting agency is not the owner (i.e. permits):<br>Corrective Action |
| Less than 1.5%  | Removal* or EA   | Removal* or EA  |
| 1.5-2.0%  | \$5.00   | EA  |
| 2.1-2.7%  | \$2.00   | EA  |
| 2.8-6.2%  | Full Payment   | No Corrective Action  |
| 6.3-6.9%  | \$2.00   | EA  |
| 7.0-8.0%  | \$5.00   | EA  |
| Greater than 8.0%   | Removal* or EA   | Removal* or EA  |

NOTES: \*The Contractor shall remove and replace the entire subplot that is deficient  
EA = Engineering Analysis per Section 321.10.6  
Removal for In-place Air Voids Greater than 11.0% is not eligible for Section 321.10.6.

If an agency or Engineer is purchasing asphalt concrete directly from a commercial material supplier, the agency or Engineer will use Section 321.10, and specifically Tables 321-3A or 321-3B as applicable, 321-4 and 321-5 from Section 321.10, when determining the acceptance of the asphalt concrete with the material supplier.

**321.10.3 Surface Testing:** If directed by the Engineer surface drainage test shall be performed. The completed

surfacing shall be thoroughly compacted, smooth and true to grade and cross-section and free from ruts, humps, depressions or irregularities. An acceptable surface shall not vary more than 1/4 inch from the lower edge of a 12-foot straightedge when the straightedge is placed parallel to the centerline of the roadway. The straightedge shall be furnished by the contractor and shall be acceptable to the Engineer.

All streets shall be water tested for drainage in the presence of the Engineer or designated representative before final acceptance. Any areas not draining properly shall be corrected to the Engineer's satisfaction at the Contractor's expense. Water for this testing shall be provided and paid for by the Contractor.

When deviations in excess of the above tolerance are found, humps or depressions shall be corrected to meet the specified tolerance, or shall be cut out along neat straight lines and replaced with fresh hot mixture and thoroughly compacted to conform with and bond to the surrounding area. Materials and work necessary to correct such deviations shall be at no additional cost to the Contracting Agency.

**321.10.4 Asphalt Pavement Thickness:** Asphalt Pavement thickness will be determined from cores secured from each lift of each subplot. Such cores will be taken and measured by the Asphalt Concrete Coring Method. This method can be found in Section [321.14](#). Each core location will be patched by the party responsible for the testing.

Acceptance or assessment of penalties for asphalt pavement thickness will be based on the combined total thickness of all asphalt concrete layers omitting all layers of asphalt-rubber asphalt concrete. If the final total pavement thickness exclusive of all ARAC layers is deficient from the target thickness by 0.25 inches or less, it will be paid for at the contract unit price.

If the pavement thickness deficiency is greater than 0.25 inches and the contracting agency is not the owner (i.e. permits) the following steps will apply:

- (1) If the thickness deficiency of the pavement exceeds 0.25 inch, the limits of the deficient area will be evaluated by coring at maximum intervals of 100 feet from the deficient core. The thicknesses of the original deficient core will be averaged with the thicknesses of the cores taken from 100 feet on each side of it to determine compliance with the acceptance requirements. If the resulting average thickness deficiency is greater than 0.25 inch, additional cores may be required to define the limits of the deficient area, and shall not be used for re-evaluating acceptance.
- (2) If the pavement thickness from step one above deviates from the target thickness by more than 0.25 inch but not more than 0.50 inch, corrective action will be required. This corrective action will consist of application of a Type II slurry seal coat in accordance to Section [715](#). The Contractor may present an engineering analysis outlining other proposed remedial measures for the consideration of the Engineer. The Engineer will review the engineering analysis and decide within 30 working days whether to accept the proposed remedial measures.
- (3) If the pavement thickness from step one above deviates from the target thickness by more than 0.50 inch, corrective action will be required. The deficient area shall be overlaid with no less than a 1 inch thick lift, for the full width of the pavement to meet or exceed the designed thickness, with appropriate end and edge milling, with a mixture approved by the Engineer. The Contractor may present an engineering analysis outlining other proposed remedial measures for the Engineer's consideration. The Engineer will review the engineering analysis and decide within 10 working days whether to accept the proposed remedial measures. If the Engineer chooses to reject the engineering analysis, the indicated overlay will be constructed by the Contractor at no additional cost to the Owner.

If the Contracting Agency is the owner and the pavement thickness deficiency is greater than 0.25 inches but less than 0.50 inches Table [321-6](#) will apply. If the pavement thickness deficiency is greater than 0.5 inches the deficient area shall be overlaid with no less than a 1-inch thick lift for the full width of the pavement to meet or exceed the designed thickness using an asphalt mixture approved by the Engineer. The Contractor shall provide appropriate end and edge milling. The overlay and milling shall be accomplished by the Contractor at no additional cost to the Contracting Agency.

| <b>TABLE 321-6</b>   |   |
|--|---|
| <b>ASPHALT PAVEMENT THICKNESS PAYMENT REDUCTION</b>                                |   |
| <b>For Thickness Deficiency of More Than 0.25 inches and less than 0.50 inches</b> |   |
| <b>Total Specified Asphalt Pavement Thickness<br/>exclusive of ARAC (if any)</b>   | <b>Reduction in Payment<br/>applied to asphalt concrete<br/>except ARAC layers (if any)</b> |
| Less than 1.5 inches   | 50%   |
| 1.50 inches to 1.99 inches   | 33%   |
| 2.00 inches to 2.49 inches   | 25%   |
| 2.50 inches to 2.99 inches   | 20%   |
| 3.00 inches and over   | 17%   |

**321.10.5 Density:****321.10.5.1 Pavement 1-1/2 Inches or Less in Nominal Thickness:**

Compaction shall consist of a “Rolling Method Procedure” using an established sequence of coverage with specified types of compactors. A pass shall be defined as one movement of a compactor in either direction. Coverage shall be the number of passes as are necessary to cover the entire width being paved.

The rolling sequence, the type of compactor to be used, and the number of coverages required shall be as shown in Table [321-7](#).

| <b>TABLE 321-7</b>                                     |                          |                     |                         |                     |
|--|--------------------------|---------------------|-------------------------|---------------------|
| <b>ROLLING SEQUENCE FOR LIFT THICKNESS 1½” OR LESS</b> |                          |                     |                         |                     |
| <b>Rolling<br/>Sequence</b>                            | <b>Type of Compactor</b> |                     | <b>No. of Coverages</b> |                     |
|  | <b>Option No. 1</b>      | <b>Option No. 2</b> | <b>Option No. 1</b>     | <b>Option No. 2</b> |
| Initial  | Static Steel             | Vibrating Steel     | 1                       | 1                   |
| Intermediate   | Pneumatic Tired          | Vibrating Steel     | 4                       | 2- 4*               |
| Finish   | Static Steel             | Static Steel        | 1-3                     | 1-3                 |

\* Based on the roller pattern which exhibits the best performance.

The Contractor shall select the option for compaction and, when pneumatic-tired compactors are used will designate the tire pressure. Steel wheel compactors shall not be used in the vibratory mode for courses of one inch or less in thickness nor when the temperature of the asphaltic concrete falls below 180 degree F. Initial and intermediate compaction shall be accomplished before the temperature of the asphaltic concrete falls below 200 degree F.

Compaction will be deemed to be acceptable on the condition that the asphaltic concrete is compacted using the type of compactors specified, ballasted and operated as specified, and with the number of coverages of the compactors as specified.

**321.10.5.2 Pavement Greater than 1-1/2 Inches in Nominal Thickness:**

Achieving the required compaction is the responsibility of the contractor. The number and types of rollers is the contractor’s responsibility and shall be sufficient to meet these requirements.

In-place air voids shall be determined in accordance with AASHTO T-269 utilizing cores taken from the finished pavement. The maximum theoretical density used in the determination of in-place air voids will be the average value from the acceptance samples determined for the Lot as outlined in [321.10.1](#).

The Engineer will designate one random test location for each subplot and the acceptance laboratory will obtain one

core from that location. Regardless of subplot quantities or boundaries, a minimum of one core will be obtained per residential street and a minimum of one core per travel lane for collector and arterial streets. The outside one foot of each pass of the pavement course or any unconfined edge will be excluded from testing. The Engineer may exclude areas from the compaction lot that are not accessible by normal compaction equipment.

The Contractor will provide the traffic control to facilitate any coring operations necessary for compaction acceptance.

Cores will be taken per the Asphalt Concrete Coring Method. This method can be found in Section [321.14](#). Acceptance testing results will be furnished to the contractor within five working days of receipt of samples by the acceptance laboratory.

If the pavement density has in-place voids of 8.0% or less, the asphalt concrete will be paid for at the contract unit price. If the pavement density has in-place voids greater than 8.0%, the deficient area will be evaluated within the subplot by coring at maximum intervals of 100 feet from the deficient core(s). If both cores in a subplot are deficient, 3 to 4 additional cores may be necessary to re-evaluate acceptance. The in-place voids of all the original core(s), whether deficient or acceptable, will be averaged with the in-place voids of the cores taken for re-evaluation to determine compliance with the acceptance requirements. If the average of the in-place voids is greater than 8.0% then Table [321-8](#) shall apply to the subplot. Additional cores may be required to define the limits of the deficient area, and shall not be used for re-evaluating acceptance.

| <b>TABLE 321-8</b>  |  |   |
|---|--|---|
| <b>PAVEMENT DENSITY PENALTIES</b>   |  |   |
| Limits of In-place Air Voids for design lift thicknesses 1.5 inches and greater | When the contracting agency is the owner:<br><br>Payment Reduction<br>(\$ per ton of asphalt concrete) | When the contracting agency is not the owner (i.e. permits):<br><br>Corrective Action |
| Below 3.0%  | Removal* or EA   | Removal* or EA  |
| 3.0% to below 4.0%  | \$10.00  | EA and Type II Surry Seal   |
| 4.0% to 8.0%  | Full Payment   | No Corrective Action  |
| Greater than 8.0% to less than 9.0%   | \$6.00   | EA  |
| 9.0% to 10.0%   | \$10.00  | EA and Type II Surry Seal   |
| Greater than 10.0%  | Removal* or EA   | Removal* or EA  |

NOTES: \*The Contractor shall remove and replace the entire subplot that is deficient.

EA = Engineering Analysis per Section [321.10.6](#)

Removal for In-place Air Voids greater than 11.0% is not eligible for Section [321.10.6](#).

**321.10.6 Engineering Analysis (EA):** Within 10 working days after receiving notice that a lot or subplot of asphalt concrete is deficient and is found to fall within the “Removal or EA” band per Table(s) [321-4](#), [321-5](#), and/or [321-8](#) the contractor may submit a written proposal (Engineering Analysis) to accept the material in place at the applicable penalties along with possible remediation(s) listed in the “Removal or EA” category. Engineering Analysis can also be proposed for non-removal categories of “Corrective actions” when the contracting agency is not the owner (i.e. permits).

The Engineering Analysis shall contain an analysis of the anticipated performance of the asphalt concrete if left in

place. The Engineering Analysis shall also detail the effect of any proposed corrective action to the material(s) in place as it relates to the in-place material's performance. The Engineering Analysis shall be performed by a professional engineer experienced in asphalt concrete testing and mix designs.

If a lot or subplot is accepted for referee testing and the referee test results still show a deficiency, the contractor shall have ten working days to submit an engineering analysis beginning upon notification of referee test results.

When an Engineering Analysis recommends that a specific lot or subplot should not be removed, the Engineering Analysis will recommend that the following penalties (Table [321-9](#)) be paid when the contracting agency is the owner, for the specific criteria being reviewed by the EA.

| <b>TABLE 321-9</b>  |                                      |  |
|---|--------------------------------------|--|
| <b>ENGINEERING ANALYSIS PENALTIES for REMOVAL* LOTS/SUBLOTS LEFT IN-PLACE</b> |                                      |  |
| <b>Acceptance Criteria</b>  | <b>Acceptance Limits</b>             | <b>Penalty When Contracting Agency is the Owner (\$/Ton)</b> |
| Asphalt Binder Content  | Over 0.2% points from that Permitted | \$9.00   |
| Laboratory Air Voids (Measured at $N_{des}$ or 75 blows as applicable)        | Less than 1.5% or Greater Than 8.0%  | \$7.50   |
| Limits of In-place Air Voids  | Less than 3% or Greater than 10.0%   | \$15.00  |

Within 15 working days, the Engineer will determine whether or not to accept the contractor's proposed Engineering Analysis.

### **321.11 REFEREE:**

If the Contractor has reason to question the validity of any of the acceptance test results, the Contractor may request that the Engineer consider referee tests for final acceptance. Any request for referee testing must describe the contractor's reasons for questioning the validity of the original acceptance test results and must clearly describe which set of acceptance tests are in question. The engineer may either accept or reject the request for referee testing. When referee testing is accepted, the Contractor (at the Contractors own expense) will engage an independent laboratory accredited by the AAP or a laboratory listed in the current ADOT Directory of Approved Materials Testing Laboratories as appropriate for the acceptance tests that are being questioned. The independent referee laboratory shall use properly certified technicians in accordance with ASTM D3666, Section 7 (Personnel Qualifications). For the set of test results in question the referee laboratory shall perform a new set of acceptance tests (as required by Section [321.10](#) representing the area for the set of tests in question). The referee tests will replace the original acceptance tests that were in question.

These tests may include asphalt binder content, aggregate gradation, Marshall or Gyratory unit weight, maximum theoretical unit weight, laboratory air voids and in-place air voids (compaction). Samples for referee testing shall come from representative samples obtained from the completed pavement, as directed by the Engineer.

The number of samples taken will be the same as specified in Section [321.10](#). The independent laboratory shall compile the test results and transmit them to both the Engineer and the contractor. The independent laboratory shall include a report sealed and signed by an Engineer registered in the State of Arizona, who is experienced in asphalt concrete testing and mix design development. The signed report shall give an opinion that the material evaluated does or does not comply with project specifications, shall clearly describe any deficiencies, and the results will be binding between all parties.

### **321.12 MEASUREMENT:**

Asphalt concrete pavement will be measured by the ton, or by the square yard, for the mixture actually used as



allowed above, which shall include the required quantities of mineral aggregates, asphalt binder, and mineral admixture. Measurement shall include any tonnage used to construct intersections, roadways, streets, or other miscellaneous surfaces indicated on the plans or as directed by the Engineer.

### **321.13 PAYMENT:**

The asphalt concrete measured as provided above will be paid for at the contract price per ton or square yard, as adjusted per Section [321.10](#), which price shall be full compensation for the item complete, as herein described and specified.

Payment for tack coat will be by the ton diluted, based on the rate of application, as directed by the Engineer.

No payment will be made for any overrun in quantity of asphalt concrete in excess of 10 percent based on actual field measurement of area covered, design thickness, and the mix design unit weight. The calculations and payment for overrun will be by individual pay item. To compensate or adjust for a thickness deficiency in an underlying asphalt concrete course, the Engineer may authorize a quantity increase in excess of 10 percent for a subsequent asphalt concrete course. In such cases, the quantity in excess of 10 percent will be paid for at the lowest unit price.

Agency required repairs of existing pavement prior to roadway overlay operations will be paid for as a separate pay item.

Except as otherwise specified, no separate payment will be made for work necessary to construct miscellaneous items or surfaces of asphalt concrete.

### **321.14 ASPHALT CORE METHOD: Core Drilling of Hot Mix Asphalt (HMA) for Specimens of 4" or 6" diameter**

**321.14.1 Scope:** This method is to establish a consistent method of the use of a diamond bit core to recover specimens of 4 or 6 inch diameter for laboratory analysis and testing. The method will require the use of: water, ice (bagged or other suitable type), dry ice, and a water-soap solution to be utilized when coring asphalt rubber concrete. Individuals doing the specimen recovery should be observing all safety regulations from the equipment manufacturer as well as the required job site safety requirements for actions, and required personal protective equipment.

**321.14.2 Core Drilling Device:** The core drilling device will be powered by an electrical motor, or by an acceptable gasoline engine. Either device used shall be capable of applying enough effective rotational velocity to secure a drilled specimen. The specimen shall be cored perpendicularly to the surface of pavement, and that the sides of the core are cut in a manner to minimize sample distortion or damage. The machinery utilized for the procedure shall be on a mounted base, have a geared column and carriage that will permit the application of variable pressure to the core head and carriage throughout the entire drilling operation. The carriage and column apparatus shall be securely attached to the base of the apparatus; and the base will be secured with a mechanical fastener or held in place by the body weight of the operator. The core drilling apparatus shall be equipped with a water spindle to allow water to be introduced inside of the drill stem while operating. The cutting edge of the core drill bit shall be of hardened steel or other suitable material with embedded diamond chips in the cutting surface. The core barrel shall be of sufficient diameter to secure a specimen that is a minimum of four or six inches or whichever is prescribed for necessary testing. The core barrel shall not be missing more than one of the teeth used for cutting; if so it shall be discarded and another barrel shall be used. The core barrel shall also be a minimum of two inches longer than the anticipated depth of pavement in accordance with project paving plans.

**321.14.3 Accessory Equipment:** A sufficient supply of ice and dry ice shall be provided to sufficiently cool the pavement prior to securing the samples from the designated areas in the pavement. The ice should also be used to adjust the temperature of the water used to cool the core bit. A water supply (usually a plastic 35 – 55 gal drum) with sufficient hose to introduce the water into and through the spindle of the coring device by gravity feed. The drum should be white or light in color to minimize excessive thermal heating of the water (*for coring of asphalt rubber cores see Note 1*). At no time shall the water utilized in the coring operation exceed 65° F during the coring operation. Ice shall be utilized to ensure the temperature control of the water being introduced during the cutting



operation. An ice chest or other suitably insulated container that can maintain a temperature of less than 70° F shall be used to secure the specimens during transport. The container will be equipped with flat shelving that will support the drilled cores throughout the entire specimen dimension during transport back to the testing facility.

Miscellaneous hand tools to remove the drilled specimen from the drill hole or the core barrel taking great care in not disturbing the specimen more than necessary (refer to fig. 1 in ASTM D5361).

**321.14.4 Process:** The pavement surface at the time of coring shall not exceed a temperature of 90° F; the pavement shall be conditioned with ice or dry ice to ensure that this requirement is met. Immediately after it has been ensured that the pavement has dropped to the required temperature, core drilling shall begin. The operator will then apply an even and continuous pressure (Note 2) to penetrate through the full depth of the pavement. The operator will concurrently ensure that enough water is moving over the core surface as to adequately remove any and all cuttings that could damage the drilled core. After the pavement thickness has been penetrated the core shall be carefully removed from either the drill hole or the core barrel and be immediately transferred to an ice chest or other suitable container. Each individual core shall be placed on a shelf in the cooler with the exposed side of the specimen facing down, or the “top side” down. If the specimen is a two lift core, the only acceptable means of separating lifts is with a power or other acceptable wet saw type of equipment (conforming to ASTM D5361); however, at no time shall cores be split using a mallet and screwdriver or metal straight edge when being tested for bulk density. Perpendicularity of the specimen shall be checked in the field after the specimen has been extracted from the surface. The core operator shall hold the core up to eye level and place the core top side down in a “speed square” or small carpenters square. The specimen placed in the square shall not depart from perpendicular to the axis more than 0.5° (approximately equivalent to 1/16 of an inch in 6 inches). If the specimen is outside of this distance from square it shall be discarded in the field and another sample cored that falls within tolerance. The cores upon arriving at the laboratory for testing shall be carefully cleaned and measured for thickness in accordance with ASTM D3549. A speed square shall be utilized to measure perpendicularity as compared to a 90° degree angle and shall not depart from perpendicular to the axis more than 0.5° (approximately equivalent to 1/16 of an inch in 6 inches). All remaining testing shall be done within the parameters of the current project and / or agency required specification.

---

\*Note 1 – It should be noted that when the material to be cored is a rubberized asphalt mixture a wetting agent such as liquid dish soap shall be added to the water barrel to hinder the material from sticking or allowing the binder to spread during coring.

\*Note 2 – This refers to pressure exerted on the core barrel and machine during the coring process. Too much pressure can cause damage to the core barrel and the motor; and too little pressure can cause a glazing of the diamonds, reducing cutting efficiency and premature wear of the barrel

*- End of Section -*